

CLAIMS

1. An all-solid-state electrochemical generator (1) comprising a negative electrode (4) capable of delivering a lithium cation, an all-solid-state polymeric electrolyte (3) formed from a macromolecular material in which an ionized lithium salt is dissolved and a positive electrode capable of incorporating the nonionized species corresponding to said lithium cation, characterized in that the all-solid-state polymeric electrolyte comprises one or more fluoropolymers in a macromolecular material/fluoropolymer(s) mass ratio of between 6 and 700.
2. The all-solid-state electrochemical generator as claimed in claim 1, characterized in that the all-solid-state alkaline polymeric electrolyte comprises 0.1 to 10 wt% of fluoropolymer(s).
3. The all-solid-state electrochemical generator as claimed in claim 1, characterized in that the all-solid-state alkaline polymeric electrolyte comprises 0.5 to 5 wt% of fluoropolymer(s).
4. The all-solid-state electrochemical generator as claimed in one of claims 1 to 3, characterized in that the fluoropolymer is chosen from the group comprising the following polymers: PVDF, PHFP, PCTFE, PTFE, PVF<sub>2</sub>, PVF.
5. The all-solid-state electrochemical generator as claimed in one of claims 1 to 4, characterized in that the positive electrode is made of a composite material, of the active substance, of a compound inert to electronic conduction favoring the transfer of electrical charges into a collector, such as graphite or acetylene black, and of the polymeric electrolyte.



that the macromolecular material of the all-solid-state polymeric electrolyte is a polyether based on polyethylene oxide or polypropylene oxide, or polyoxyalkylenes.

5

12. The all-solid-state electrochemical generator as claimed in one of claims 1 to 11, characterized in that the negative electrode is a lithium electrode.

10

13. The all-solid-state electrochemical generator as claimed in one of claims 1 to 12, characterized in that the polymeric electrolyte comprises magnesia, preferably 5 to 30 wt%, very advantageously between 8 and 25 wt%.

15

14. The all-solid-state electrochemical generator as claimed in one of claims 1 to 13, characterized in that the macromolecular material of the all-solid-state polymeric electrolyte is formed by extrusion or by coextrusion with the electrode films.

20

15. The all-solid-state electrochemical generator as claimed in one of claims 1 to 14, characterized in that the polymeric electrolyte comprises an antioxidant compound.

25

16. The all-solid-state electrochemical generator as claimed in claim 15, characterized in that the proportion of antioxidant compound is between 0.5 and 3% with respect to the mass of polymer.

30

17. The all-solid-state electrochemical generator as claimed in either of claims 15 and 16, characterized in that the oxidant is chosen from the group comprising quinone or hydroquinone derivatives and phenolic antioxidants.

35

- 14 -

18. An all-solid-state polymeric electrolyte formed from a macromolecular material in which an ionized lithium salt is dissolved, and comprising one or more fluoropolymers, as defined in claims 1 to 17, which is useful, in particular, for producing all-solid-state electrochemical generators as claimed in one of claims 1 to 17, in which the macromolecular material/fluoropolymer(s) mass ratio is between 6 and 700.